





















# TECHNICAL INFORMATION

## Greenfelt 22dB

# ntgrate®

		composition	78% PVC – 7% glass fibre – 15% PET	
		wear layer	Reinforced PVC glass fibre	
			TILES	ROLLS
	ISO 1765	<b>thickness</b>	5,2 mm / 0,20 inch	5,2 mm / 0,20 inch
	ISO 8543	<b>weight</b>	3,2 kg/m <sup>2</sup> / 94,38 oz / yd <sup>2</sup>	3,2 kg/m <sup>2</sup> / 94,38 oz / yd <sup>2</sup>
	EN 1307	<b>level of use</b>	class 33	class 33
	EN 985	<b>castor chairs</b>	intensive use	intensive use
	ISO 1815	<b>static loading</b>	< 2 kV	< 2 kV
	EN13893 DIN 51130	<b>slip resistance</b>	> 0,3 R9	> 0,3 R9
	ISO 10140	<b>impact sound ΔLw</b>	22 dB	22 dB
	ISO 354	<b>acoustical absorption</b>	class E Δw= 0,15	class E Δw= 0,15
	EN 16205	<b>drum sound</b>	67 dB (A)	67 dB (A)
	EN 105-B02	<b>light fastness</b>	≥ 7	≥ 7
	EN 13501	<b>reaction to fire</b>	Bfl-s1	Bfl-s1
	ASTM E648-17 NFPA	<b>critical radiant flux</b>	0,63 W/cm <sup>2</sup> Class 1	0,63 W/cm <sup>2</sup> Class 1
	ASTM E662-15A	<b>smoke density</b>	< 450	< 450
	EN 984	<b>dimensions</b>	500 x 500 mm 19,69 x 19,69 inch	500 x 500 mm 19,69 x 19,69 inch
	ISO 24341	<b>width</b>	500 mm / 19,69 inch	200 – 202 cm / 7,87 – 7,95 inch
	ISO 10965	<b>length</b>	500 mm / 19,69 inch	on demand
	EN 986	<b>dimensional stability</b>	< 0,2 %	< 0,2 %
	EN 1814	<b>resistance to fraying</b>	very good	very good
	EN 423	<b>staining resistance</b>	very good	very good
	EN 15114	<b>humid conditions</b>	suitable	suitable
	ISO 8302	<b>thermal resistance (underfloor)</b>	suitable	suitable
	EN 14.041	<b>Dop nr.</b>	0493-CPR-0193	0493-CPR-0194

ntgrate  
is green.  
– discover our  
green and  
VOC emissions  
certificates



BREEM®



CERTIFIED BY  
SCS Global Services



Edition 07-06-2022